

PROPACO SC

«WASHABLE» CORROSION-PREVENTIVE
AND SCRATCHPROOF PROTECTION
CAMOUFLAGE PRODUCT

Approvals :

French AIR FORCE (STPA), DASSAULT, AIRBUS INDUSTRIE (AIMS 04.04.015)

A temporary protection compound quickly drying and forming an adhesive film particularly resistant to scratches, bad weather, saline or corrosive atmospheres, acid vapours, water, grease, oil and hydrocarbon spray.

PROPACO SC is intended for painted or unpainted metallic assemblies and may be applied by spray gun or preferably by means of a varnishing brush.

PROPACO SC is a safe product strictly free of harmful benzene or chlorinated hydrocarbons. Also available on request tinted in "BF4 grey" **PROPACO SG**.

DIRECTIONS FOR USE

The application equipment must be clean, dry and cleared of oil or solvent contamination. The substrates to be protected must be degreased and dried.

The product is ready for use. After storage, it is advised to shake the product to obtain complete homogenisation. It is usable cold and pure by brush. If necessary, it can be applied by classical, HVLP or airless spray gun (nozzle > 22, pressure 5-6 bars) or by dipping. If a particular application viscosity is required, adjust it with suitable **DIESTONE** thinners.

Covering takes about 10 to 15 min per layer. If a greater thickness is required, apply several thin layers at 30min intervals between each one. The film achieves its final hardness characteristics after 12 to 24 hours drying at ambient temperature (or in 1 hour by stoving at 50-60° C / 122-140° F).

Before drying, the application equipment can be cleaned with clear water. After polymerisation, use either water with **SYNCLAIR A, A2, A/C** (20 %), or suitable **DIESTONE** diluents.

Socomor
Finishing Technologies

Support technique International / International Technical Support
tel. +33 (0)2 97 43 76 90 fax +33 (0)2 97 54 50 26 E-mail Support@socomor.com

*Veillez consulter notre site Web pour connaître notre correspondant le plus proche
Please consult our Web site to find our nearest correspondent*

socomor@socomor.com



REMOVAL

It is easily strippable by means of cleaning solvents (such as **DIESTONE** or **DN 108**) or alkaline aqueous solutions (**SYNCLAIR A, A2, A/C** and **SYNCLAIR A2 GEL**). If necessary, a strippable overprotection called **PELLIMER SE/2** may be applied which can be separately removed.

By means of alkaline cleaners:

The use of alkaline cleaners «SYNCLAIR» offers many advantages: non flammable, will not damage painted or unpainted materials or plastics, absence of unpleasant odours and vapours, biodegradability.

In bath, SYNCLAIR A will preferably be used at 20 to 30 % in water. By spraying, SYNCLAIR A2 GEL is the most economical product because of its thixotropy. Apply it pure by simple spraying with a classical or airless spray gun ; use the product at a temperature between 20 and 35° C (68-95° F) (at a temperature higher than 40° C / 104° F, the gel may dry prematurely). When applying SYNCLAIR A2 GEL, start the spraying from the bottom of the vertical surfaces to the top in order to avoid the formation of bad edges. After 20 minutes contact, rinse by flushing under pressure, with hot water.

By means of cleaning solvents:

The use of cleaning solvents may be interesting in case of finishing or stripping operation just before painting the protected metals. Preferably use DIESTONE. When the work or the premises location requires a non flammable diluent at an ordinary temperature, use DN 108.

If PROPACO SC itself requires to be cleaned without stripping the protection film, use the diluents-degreasers HYSO 96/1 or HYSO 99, which are not aggressive on the dry film of PROPACO SC.

TECHNICAL CHARACTERISTICS

. COMPOSITION	aqueous-alcoholic solution of synthetic resins and corrosion-preventive pigments.
. Appearance	thixotropic liquid
. Colour	beige
. Flammability point (ISO 2592).....	> 100° C (212° F)
. Covering power	10 to 12 m ² /l (according to porosity)
. Average thickness per layer	20 to 30 microns
. Application temperature	5 to 35 °C (41 to 95 °F)
. Product stability in storage	5 to 40 °C (41 to 104 °F)
. Salt spray ASTM B117-94 (alloy 2024)	≥ 500 hours

STORAGE AND USE SAFETY MEASURES

Store and handle far from flames and heat sources.

Please consult the safety data sheet for further information.

This technical data sheet replaces and cancels the previous one.

The above details have been compiled to the best of our knowledge, they have, however, an indicative value only, and we therefore make no warranties and assume no liability in connection with any use of this information, particularly if a third party's rights are affected by the use of our products. The above information has been compiled based upon tests carried out by SOCOMOR ; all data is subject to change as Socomor deems appropriate. The data given is not intended to substitute for any testing you must conduct in order to determine the suitability of the product for your particular purposes. Please check your local legislation applicable to the use of this product. Should you need any further information please contact our services.

Socomor
Finishing Technologies

Support technique International / International Technical Support
tel. +33 (0)2 97 43 76 90 fax +33 (0)2 97 54 50 26 E-mail Support@socomor.com

*Veillez consulter notre site Web pour connaître notre correspondant le plus proche
Please consult our Web site to find our nearest correspondent*

socomor@socomor.com

